

TEST REPORT

No. : XMIN2102001299CM

Date : Jul 23, 2021

Page: 2 of 3

Sample Information:

Flooring, See the photographs.

Lab environment condition: 23±2°C, 50±5%RH


Preconditioning: 23±2°C, 50±5%RH for a minimum of 24h

Test Result(s):

No.	Test item(s)	Test method(s)	Test condition	Test result(s)
1	Locking strength	ISO 24334:2014	Specimen: 10 pieces of long side (X direction) specimens 200mm×182mm, 10 pieces of short side (Y direction) specimens 200mm×182mm Loading rate: 0.5 mm/min	Long side(X): 4.0 kN/m Short side(Y): 3.0 kN/m
2	Peel Strength	ASTM D903-98(2017)	Specimen width:25mm Separation speed:152mm/min	X direction:70.6N/25mm Y direction:66.2N/25mm
3	Light Ageing Test-Xenon-arc Exposure	ASTM F1515-15 & ASTM F3261-20 section 8.6	/	See annex A

Note: All test specimens were cut from the samples, see the photographs.

Original Sample Photo:



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 | (86-592) 5765857 | (86-592) 5765380 | e sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001299CM

Date : Jul 23, 2021

Page: 3 of 3

Annex A:

Test Item: Light Ageing Test-Xenon-arc Exposure

Sample Description: See photo

Test Method: ASTM F1515-15 & ASTM F3261-20 section 8.6

Test Condition:

Exposure cycle:

Irradiance: 0.30 W/(m²·nm)@340 nm

Continuous light at (63±2) °C BPT, (50±10) %RH

Filter: Window

Exposure period: 300 h

Test Result:

Sample	ΔE^*_{ab} (see table 1)	Requirement in ASTM F3261-20 section 8.6	Conclusion
A	1.3	$\Delta E^*_{ab} \leq 8.0$	Pass

Note: ΔE^*_{ab} was measured by sphere spectrophotometer under D65 standard light source and with 10° observer. The results include specular component reflection condition, 8 mm aperture.

Table 1:

Sample	Exposure period	L *	a*	b*	ΔE^*_{ab}	Average of ΔE^*_{ab}
A-1	0 h	73.44	2.91	14.59	1.3	1.3
	300 h	74.43	2.23	14.97		
A-2	0 h	75.16	2.80	16.99	1.4	
	300 h	76.23	2.19	17.54		
A-3	0 h	74.89	2.91	16.76	1.2	
	300 h	75.79	2.35	17.39		

Note: The test results were transferred from report No.: XMIN2102001295CM dated: Jul 23, 2021 issued by SGS.

***** End of report*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 6307 1443, or email: CN.Desuhs@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com