

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 2 of 8

Sample information:

Flooring, See the photograph.

Lab environment condition: 23±2°C, 50±5%RH

Preconditioning: 23±2°C, 50±5%RH for a minimum of 24h

Test result(s):

Sample nominal size: 1524mm×182mm×5mm

No	Test item(s)	Test method(s)	Test condition	Test result(s)
1	Length	ASTM F3261-20 Section 7.2&7.4 & ASTM F2055-17	Specimen: 1524mm×182mm×5mm, 5pcs	Average: 1524mm(60.000in.) Tolerance: 0.0mm(0.000in.)
	Width			Average: 181.94mm(7.163in.) Tolerance: 0.00mm(0.000in.)
	Squareness			Deviation range: 0.00mm(0.000in.)~+0.10mm(+0.004in.)
2	Length	ASTM F2421-05(2011)	Specimen: 1524mm×182mm×5mm, 5pcs	Average: 1524mm(60.000in.) Tolerance: 0.0mm(0.000in.)
	Width			Average: 181.92mm(7.162in.) Tolerance: 0.00mm(0.000in.)
	Squareness			Deviation range: 0.00mm(0.000in.)~+0.10mm(+0.004in.)
3	Flatness	ASTM F3261-20 Section 7.2, 7.5, 7.6, 7.7 & ISO 24337:2019	Specimen: 1524mm×182mm×5mm, 5pcs	$F_{I\ concave} = -0.01\%$ $F_{I\ convex} = +0.00\%$ $F_{W\ concave} = -0.03\%$ $F_{W\ convex} = no\ convex$
	Openings			$O_{avg} = 0.00\ mm(0.000in.)$ $O_M = 0.05\ mm(0.002in.)$
	Ledging			$H_{avg} = 0.00\ mm(0.000in.)$ $H_M = 0.05\ mm(0.002in.)$



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing request for report & certificate, please contact us at telephone: (86-755) 83871443, or email: CN.Check@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬 | 翔安区翔虹路31号 邮编: 361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 3 of 8

No	Test item(s)	Test method(s)	Test condition	Test result(s)		
4	Thickness	ASTM F3261-20 Section 7.3.1 & ASTM F387-17	Specimen: 150mm×150mm×5mm, 5pcs	Average: 5.09mm(0.200in.) Deviation from nominal size: +0.07mm(+0.003in.) ~+0.12mm(+0.005in.)		
5	Thickness of wear layer	ASTM F3261-20 Section 4.1.2, 7.3.2 & ASTM F410-08(2017)	Specimen: 13mm×50mm×5mm, 5pcs	Average: 0.535mm(0.021in.) Maximum: 0.545mm(0.021in.) Minimum: 0.527mm(0.021in.)		
6	Residual Indentation	ASTM F3261-20 Section 8.1 & ASTM F1914-18	Specimen: 51mm×51mm×5mm, 3pcs Diameter of indenter: 6.35±0.0127mm Condition: 23±2°C, 50±5%RH, 24h →75±0.75 lb, 15min →Recovery time: 60min	0.04mm (0.002in.)	0.04mm (0.002in.)	0.04mm (0.002in.)
				Average: 0.04mm(0.002in.)		
7	Surface integrity	ASTM F3261-20 Section 8.2 & ASTM F1914-18	Specimen: 51mm×51mm×5mm, 3pcs Diameter of indenter: 4.521±0.0127mm Condition: 23±2°C, 50±5%RH, 24h →140±1 lb, 10min	No puncture through wear layer		
8	Dimensional stability (see note 2)	ASTM F3261-20 Section 8.3 & ASTM F2199-20	Specimens: 305mm×182mm×5mm, 3pcs Condition: 23±2°C, 50±5%RH, 24h →70°C, 360min→ 23±2°C, 50±5%RH, 24h	Average: Length Direction (X): 0.02% Width Direction (Y): 0.02%		
9	Curling (see note 3)			Average: Curling _{value} : 0.27mm(0.011in.) Curling _{max} : 0.40mm(0.016in.)		



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing registration report & certificate, please contact us at telephone: (86-755) 6337 1443, or email: CN.Despatch@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬 | 翔安区翔虹路31号 邮编: 361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 4 of 8

No	Test item(s)	Test method(s)	Test condition	Test result(s)		
10	Resistance to chemicals	ASTM F3261-20 Section 8.4 & ASTM F925-13(2020)	Specimen: 500mm×182mm×5mm, 1pc Condition: 23±2°C, 50±5%RH, 24h Drop Method, Cover, 60±1min	Rating 0: No change (see note 2) (see the Table 1)		
11	Resistance to heat	ASTM F3261-20 Section 8.5 & ASTM F1514-19	Specimen: 500mm×182mm×5mm, 3pcs Condition: 23±1°C, 50±5%RH, 24h →70±1°C, 7days→ 23±1°C, 50±5%RH, 1h	Average ΔE^*_{ab} : 0.81 Max ΔE^*_{ab} : 1.05 (see note 2)		
12	Static Load (Residual Indentation)	ASTM F3261-20 Section 8.7 & ASTM F970-17	Specimen: 60mm×60mm×5mm, 3pcs Diameter of indenter: 28.6mm Condition: 23±2°C, 50±5%RH, 24h →250lb, 24h →Recovery time: 24h	0.11mm (0.004in.)	0.07mm (0.003in.)	0.09mm (0.004in.)
				Average: 0.09mm (0.004in.)		
13	Thickness swell	ASTM F3261-20 Section 8.8	Specimen: 150mm×150mm ×5mm, 4pcs	With backing: 0.16% Without backing: 0.09%		
14	Light Ageing Test- Xenon-arc Exposure	ASTM F1515-15 & ASTM F3261-20 section 8.6	/	See the Table 2		



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8387 1443, or email: CN.Check@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬 | 翔安区翔虹路31号 邮编: 361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 5 of 8

- Note: 1. All test specimens were cut from the samples, see the photograph.
 2. Sphere Spectrophotometer with an 8 mm diameter opening having a daylight light (D-65) sources that measure color in CIE L*, a*, b*, ΔE*ab using CIE 10° Standard Observer and Specular Included.
 3. Dimensional stability, % = (The average final length – The average initial length)/The average initial length×100.
 4. Curling, mm = Dimension after exposure to heat - Dimension before exposure to heat.
 5. 1 in.=25.4 mm.
 6. Standard requirement of ASTM F3261-20 for the test items:

Characteristic	Requirement	
	Residential	Commercial
Size, tolerance Up to 12 in.(305mm); >12in. ≤18in.(457mm) >18in.	±0.016in.(0.40mm) ±0.018in.(0.45mm) ±0.020in.(0.50mm)	±0.016in.(0.40mm) ±0.018in.(0.45mm) ±0.020in.(0.50mm)
Squareness	max 0.010 in.(0.25mm)	max 0.010 in.(0.25mm)
Size, tolerance Plank length, ≥24 in. (610mm) <48in. >48in. (1220mm)	±0.060in.(1.5mm) ±0.080in.(2mm)	±0.060in.(1.5mm) ±0.080in.(2mm)
Flatness, max, inches , max % width , max % length	$F_w \pm 0.008in. (0.2mm)$ for planks or tiles ≤9 in.(229mm) wide $F_w \text{ concave} \leq 0.15 \% / F_w \text{ convex} \leq 0.20 \%$ for all other widths $F_l \text{ concave} \leq 0.15 \% / F_l \text{ convex} \leq 0.20 \%$	$F_w \pm 0.008in. (0.2mm)$ for planks or tiles ≤9 in.(229mm) wide $F_w \text{ concave} \leq 0.15 \% / F_w \text{ convex} \leq 0.20 \%$ for all other widths $F_l \text{ concave} \leq 0.15 \% / F_l \text{ convex} \leq 0.20 \%$
Openings, avg / max, mm	$O_{avg} \leq 0.004 in. (0.1mm) / O_M \leq 0.008 in. (0.2mm)$	$O_{avg} \leq 0.004 in. (0.1mm) / O_M \leq 0.008 in. (0.2mm)$
Ledging, avg / max, mm	$H_{avg} \leq 0.004 in. (0.1mm) / H_M \leq 0.006 in. (0.15mm)$	$H_{avg} \leq 0.004 in. (0.1mm) / H_M \leq 0.006 in. (0.15mm)$
Thickness, product without foam with foam back layer	as specified ±0.005 in.(0.13mm) as specified ±0.008 in.(0.20mm) min 0.080 in. (2.0mm)	as specified ±0.005 in.(0.13mm) as specified ±0.008 in.(0.20mm) min 0.080 in. (2.0mm)
Residual indentation, in.	Avg. ≤ 0.007 in. (0.18 mm)	Avg. ≤ 0.007 in. (0.18 mm)
Surface integrity	No puncture through wear layer/décor layer into rigid core	No puncture through wear layer/décor layer into rigid core
Resistance to chemicals	No more than a slight change in surface dulling, surface attack, or staining	No more than a slight change in surface dulling, surface attack, or staining
Resistance to heat	ΔE < 8 avg, max	ΔE < 8 avg, max
Resistance to light	ΔE < 8 avg, max	ΔE < 8 avg, max



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-156) 6371443, or email: CN.Checkback@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 6 of 8

Table 1: Resistance to Chemicals

No.	Reagents	Surface Dulling	Surface Attack	Color Change	Comments	ΔE^*_{ab}
1	White vinegar (5% acetic acid, AR)	0	0	0	no staining or other visible defects	0.26
2	Rubbing alcohol (70% isopropyl alcohol, AR)	0	0	0	no staining or other visible defects	0.12
3	White mineral oil (medicinal grade)	0	0	0	no staining or other visible defects	0.78
4	NaOH solution (5%, AR)	0	0	0	no staining or other visible defects	0.36
5	HCl solution (5%, AR)	0	0	0	no staining or other visible defects	0.22
6	H ₂ SO ₄ solution (5%, AR)	0	0	0	no staining or other visible defects	0.41
7	Household ammonia solution (5% NH ₄ OH, AR)	0	0	0	no staining or other visible defects	0.24
8	Household bleach (5.25% NaClO AR)	0	0	0	no staining or other visible defects	0.24
9	Disinfectant—phenol type (5 % active phenol)	0	0	0	no staining or other visible defects	0.16
10	Kerosene	0	0	0	no staining or other visible defects	0.12
11	Olive oil	0	0	0	no staining or other visible defects	0.49
12	Unleaded gasoline	0	0	0	no staining or other visible defects	0.27

Note: Subjective category ratings will all utilize the same scale of 0-3 refer to ASTM F925-13(2020), as follows:

Rating	Appearance
0	no change
1	slight change
2	moderate change
3	severe change



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at cn@sgs.com (86-592) 5765857, or email: CN.Inspection@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com
 中国·福建·厦门·火炬 | 翔安区翔虹路31号 邮编: 361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com

TEST REPORT

No. : XMIN2102001297CM

Date : Jul 23, 2021

Page: 7 of 8

Table 2:

Test Item: Light Ageing Test-Xenon-arc Exposure

Sample Description: See photo

Test Method: ASTM F1515-15 & ASTM F3261-20 section 8.6

Test Condition:

Exposure cycle:

Irradiance: 0.30 W/(m²·nm)@340 nm

Continuous light at (63±2) °C BPT, (50±10) %RH

Filter: Window

Exposure period: 300 h

Test Result:

Sample	ΔE^*_{ab} (see table 1)	Requirement in ASTM F3261-20 section 8.6	Conclusion
A	1.4	$\Delta E^*_{ab} \leq 8.0$	Pass

Note: ΔE^*_{ab} was measured by sphere spectrophotometer under D65 standard light source and with 10° observer. The results include specular component reflection condition, 8 mm aperture.

Table 1:

Sample	Exposure period	L *	a*	b*	ΔE^*_{ab}	Average of ΔE^*_{ab}
A-1	0 h	63.19	5.76	20.33	1.5	1.4
	300 h	64.14	5.06	21.22		
A-2	0 h	63.41	5.20	19.69	1.3	
	300 h	64.29	4.47	20.31		
A-3	0 h	66.03	5.33	20.57	1.3	
	300 h	66.89	4.49	21.03		



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8387 1443, or email: CN.Qeccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | (86-592) 5765857 | (86-592) 5765380 | www.sgs.com.cn
 中国·福建·厦门·火炬 | 翔安 | 翔安火炬路31号 | 邮编: 361101 | (86-592) 5765857 | (86-592) 5765380 | sgs.china@sgs.com


TEST REPORT

No. : XMIN2102001297CM


Date : Jul 23, 2021

Page: 8 of 8

Test Photo:



Specimen photograph(s):



Note: The test results were transferred from report No.: XMIN2102001293CM dated: Jul 23, 2021 issued by SGS.

*****End of report*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgs.com.cn
 中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com